

## ALJAZEERA

industrial Ready mix factory مصنـع الجزيــرة الصنـاعيــة لأنتــاج الخرسانــة

- ✓ info@jazeerakw.com
- **L** +965 9222 6858 +965 9994 006
- @jazeera.kw
- kabad Block B Building 7

٢	عن الشركة	.1
0	المهمة و الرؤية	.2
٧	مراقبة الحودة	.3
٨	سياسة الصحة و السلامة	.4
9	السياسة البيئية	.5
- 11	مصانع غسيل الرمال	.6
- 11	المعدات و القدرات	.7
۱۳	اوراق المصنع	.8
	1) غرفة التجارة والصناعة	
	2) ترخيص المصنع	
	3) اعتماد المصنع في وزارة الأشغال	
١٧	اعتماد الخلطات التصميمية في وزارة الدفاع	.9
۲٦	اعتمادات موردين المواد الأولية في وزارة الأشغال	.10
۲۷	الاعتمادات مورد الأسمنت	.11
	1) وزارة الأشغال و وزارة الدفاع	
۱۳	اعتماد مصدر الصلبوخ -احجار انترناشونال مع وزارة الاشغال (كيميائي	.12
	+ فيزيائي)	
٤٠	اعتماد مصدر المادة المضافة في وزارة الأشغال	.13
	1)  فحوصات (كيميائي+ فيزيائي)  وزارة الأشغال	
٤٦	فحوصات المواد الأولية في مختبر خارجي معتمد من وزارة الأشغال	.14
	1)   أسمنت عادي (كيميائي + فيزيائي)	
	2) أسمنت مقاوم (كيميائي + فيزيائي)	
	3) المادة المضافة (كيمياء+ فيزيائي)	
	4) الرمل المغسول (كيميائي + فيزيائي)	
	5)  صلبوخ ۱nch ٤/۳ (کیمیائي + فیزیائي)	
	6)  صلبوخ ۱nch ۸/۳ (کیمیائي + فیزیائي)	



## عن الشـركة

شركة الجزيرة الصناعية للتجارة العامة والمقاولات هي الشركة الأم تأسست في عام ١٩٨٣م ومقرها في دولة الكويت، حققت الكثير من الإنجازات على الصعيد المحلي والإقليمي في مجال الإنشاءات والبناء و المعدات الثقيلة والخفيفة.

تم تأسيس مصنع الجزيرة الصناعية لإنتاج وتوريد الخرسانة الجاهزة كشركه فرعية في عام ٢٠٢١م، ويهدف إلى أن يكون المصنع الأول لإنتاج الخرسانة الجاهزة في دولة الكويت.

يقوم النشاط الأساسي لمصنع الجزيرة الصناعية لإنتاج الخرسانة الجاهزة على تصنيع الخرسانة الجاهزة بمواصفاتها ذات الجودة العالية أصلا والتي تتضمن بعملائها الكرام حصولهم على أفضل أنواع الخرسانة بما يتماشى مع المواصفات العالمية للمشاريع المختلفة.



## عن الشـركة

كما يسعى مصنع الجزيرة الصناعية دائما على توريد الخرسانة لأكبر المشاريع الحكومية والخاصة من مختلف فروعها لتلبية احتياجات عملائها الكرام بما يتوافق مع أحدث مواصفات الجودة العالمية والمحلية بطاقة انتاجية تقدر بـ (١٢٠ متر مكعب / ساعة)

تمتلك الشركة العديد من أحدث المختبرات المتاحة لعملائها الكرام، والتي تزود هذه المختبرات أحدث الأجهزة وذلك بمراقبة مستمرة من قبل المهندسين ومراقبي الجودة والفنيين حسب المواصفات العالمي. ASTM&BS

يمتلك مصنع الجزيرة الصناعية أحدث الخلاطات المركزية الالمانية لإنتاج الخرسانة الجاهزة من نوع للمركزية الالمانية لإنتاج الخرسانة الجاهزة من نوع LIEBHERR alc, بالإضافة إلى ذلك يمتلك مصنع الجزيرة الصناعية أسطول كبير من الخلاطات المتحركة والشاحنات والمعدات المصنعة على أحدث ما أنتجته التكنولوجيا. وبفضل هذه الإمكانيات فإن مصنع الجزيرة الصناعية يستطيع تقديم خدماته إلى جميع عملائه بكل يسر وسهولة وفي أي مكان وزمان، وبالكميات التي يرغبها العميل، وكل ذلك مدعوم بإمكانيات بشرية على درجة عالية من مهندسين وفنيين واستشاريين وإداريين وعمال فوي كفاءة عالية وخبرة طويلة في مجال إنتاج وتصنيع الخرسانة الجاهزة.





كم عزز مصنع الجزيرة الصناعية لإنتاج الخرسانة الجاهزة أسطوله من البداية من خلال توفير مصنع ثلج ومياه مبرده ،خلاطات متنقلة من نوع مرسيدس اكتروس بجرات نوع جوريكا بسعة ١٠ م، مضخات متنقلة نوع شوينغ حجم ٤٢، ويقوم مصنع الجزيرة الصناعية بإنتاج الخرسانة الجاهزة بعمل وإجراء صيانة دورية لأسطوله من قبل فريق الصيانة الخاص بالشركة لخدمة احتياجات عملاءه الكرام.



## المهمة و الرؤية



#### **OUR MISION**

الحفاظ على مكانتنا كشركة تصنيع وتوريد رائدة في مجال الخرسانة الجاهزة، وذلك من خلال تزويد عملائنا الكرام بمنتجات عالية الجودة وخدمة محترفة.

To maintain our market position as a leading supplier and production company of ready-mix concrete to provide our customers high calibre professional service.

#### **OUR VISION**

نصبح المورد الأول للخرسانة العالية الجودة مع التطوير المستمر من أجل توفير أفضل الحلول الخرسانية في دولة الكويت.

We strive to become a leading supplier of high-quality concrete with persistent development aiming to provide the best solution of concrete in Kuwait.



### مراقبة الجودة

يهدف مصنع الجزيرة الصناعية على أن يكون المنتج والمورد الرئيسي للخرسانة الجاهزة في الكويت والجودة أساسية لهذا الهدف وهي مبدأ توجيهي في كل ما نقوم به، نحقق هذا الهدف فاصل من خلال استخدام أجود وأفضل المواد الخام المستخدمة في عمل الخرسانة تحت إشراف مراقبو جودة ذوو خبرة وحاصلون على شهادات معتمده في أختيار المواد الخام الأفضل لتصنيع الخرسانة الجاهزه.



Aljazeera Industrial factory aims to become the main producer and supplier of ready-mix concrete in Kuwait dots to achieve the same, quality is one of significance and is viewed as a guiding principle in Al Jazeera Industrial factory activities to achieve this goal al Jazeera Industrial factory uses off the best materials and latest modern factories and the state-of-the-art equipment by a professional quality control employee.

### سياسة الصحة والسلامة

يرى مصنع الجزيرة الصناعية أن صحه وسلامة موظفيه أمر مهم جدا. فهو على دراية بتحديات البيئة التشغيلية، كما نؤمن بأن خلق ثقافة الصحة والسلامة المسؤولة في جميع عمليات المصنع هو أمر له أهمية قصوى للنجاح على المدى الطويل كما نحرص على القيام بدور فعال في رفع الوعي بالصحة والسلامة أداء موظفيه وعملائه ومورديه



Al Jazeera Industrial believes that the health and safety of its employees is the most important thing that it accepts the challenges of the operational environment and believes that creating responsible health and safety culture in all of its operations for long term success .al Jazeera Industrial factory is also keen to play an effective role in rising health and safety awareness among its employees, customers and suppliers.


## السياسة البيئية

بصفتنا منتجون وموردون للمواد الخام الخرساني والخرسانة الجاهزة فاصل فإننا نتفهم أن أنشطة أعمالنا ومنتجاتنا لها تأثير بيئي وما نسعى إليه هو أن يكون هذا التأثير إيجابي. نظرتنا هي أنشطة أعمال أو منتجاتنا يجب أن يكون لها تأثير إيجابي على بيئتنا، وأن الوقاية من من التلوث يتحقق من خلال هذه النظرة التي تعتبر جزء لا يتجزأ من نجاح أعمالنا.



As a producer and supplier of concrete raw materials and readymix concrete, Aljazeera Industrial factory understands that our business activities and products have an environmental impact. therefore, Aljazeera Industrial Industrial factory strives to render such impact positive. Is there a company view is that its business activities and products should have a positive impact on our environment and that prevention of pollution is achieved through this year that is an integral part of our business success.

مصنع الجزيرة للخرسانة الجاهزة يقع مصنع الجزيرة الصناعية لإنتاج الخرسانة في موقع استراتيجي يسهل الوصول الى اي مشروع في الكويت وهو في منطقة كبد - طريق الصليبية.



Al-Jazeera Industrial Factory for Concrete Production is in a strategic location that facilitates access to any project in Kuwait, and it is located in the Kabd area – sulaibiya road.

## مصانع غسيل الرمال

تمتلك شركة الجزيرة الصناعية مصانع لغسيل الرمال حتى يتم الحصول على رمل عالي الجودة وخالي من الشواب لتلبية مواصفات الخرسانة عالية الجودة بطاقة إنتاجية عالية.

Al-Jazeera Industrial Company owns sand-washing factories to obtain high-quality sand free of impurities to meet the specifications of high-quality concrete, with an high production capacity.

## المعدات والقدرات

خلال عقود من التطور والتوسع تمكنت الشركة من الحصول على واحد من أفضل الأساطيل في المنطقة مما جعل قدرتنا تتجاوز توقعات الكثيرين، وعندما يكون هناك مشاريع تحتاج إلى قوة موثوقة لرعاية الأعمال، فإن قدراتنا ومعداتنا موجودة دائما للعملاء لإنجاز مهمتهم، فنحن نقول يمكنكم الاعتماد عليه دائما وأبدا.

Through decades of development and expansion, the company was able to obtain one of the best fleets in the region, which made our ability to exceed the expectations of many, and when there are projects that need a reliable force to take care of the business, our capabilities and equipment are always there for customers to accomplish their mission, we say you can depend on it always and forever







# اوراق المصنع

- غرفة التجارة والصناعة
  - ترخيص المصنع
- اعتماد المصنع في وزارة الأشغال

## KUWAIT CHAMBER OF COMMERCE & INDUSTRY



#### شهادة تسجيل لعام 2022

رقم الايصال: 220261250

التاريخ : 13/10/2022

### تشهد غرفة تجارة وصناعة الكويت أن

اسم العضو : مصنع الجزيرة الصناعية لانتاج الخرسانة فرع من شركة الجزيرة الصناعية للتجارة العامة والمقاولات ذم م

رقم التسجيل : 237964 الرقم المدني للجهة : 5103216

حالة العضوية : صالحة عالم عالم الترخيص :

مسجل لديها منذ عام : 2022 تاريخ التسجيل : 2022/10/13

رقم الترخيص : 12740 تاريخ التهاء الترخيص : 2027/03/28

رقم السجل التَّجاري : 324248 رأس المال :

aljazeera.co@protonmail.com : البريد الإلكتروني :

أرقام الهواتف : الموقع على الإنترنت :

صندوق بريد : العنوان :

رقم الهاتف الجوال : 90047677 الموقع : صليبية كبد ق B قسيمة 7 ملك الهيئة العامة للصناعة

لمزاولة :

\*\*\* انتاج الخرسانة الجاهزة \*\*\*



البيانات الواردة برمز (QR Code) هي البيانات المدونة لدى الغرفة عن طريق أعضائها المسجلين لديها ، ويتم استخراج شهادة التسجيل الالكتروني بناء على هذه البيانات ، وتخلي الغرفة مسئوليتها عن أي تغيير فيها بالحذف أو الإضافة ، كما ننوه بأن هذه البيانات متاحة للجميع على موقع الغرفة الالكتروني تطبيقا لمبدأي المصداقية والشفافية يرجى العلم بأن صلاحية الشهادة تنتهي في 2022/12/31



www.Kuwaitchamber.org.kw

هاتف: Tel.: (+965) 180 55 80 - افاكس: Tel.: (+965) 180 55 80 - عن ب: P.O.Box : 775 Safat (CODE: 13008)







رقم الترخيص: ١٢٧٤٠

تاريخ الترخيص: ٢٠٠٧/٠٥/٢٦

تاريخ الانتهاء: ٢٠٢٧/٠٣/٢٨

الدولة : الكويت

الهيئة: الهيئة العامة للصناعة

الادارة: مركز الخدمة المتكاملة

المنطقة: جنوب السرة

#### ترخيص مشروع صناعي (منشأه صناعية)

الكيان القانوني الجنسية نسبةالمساهمة كويتي (١٠٠٠)

اسم صاحب/اصحاب التراخيص الرقم المدني

TYPEVAT

شركة الجزيرة الصناعية للتجارة العامة والمقاولات

اسم المشروع الصناعي (الإسم التجاري):

مصنع الجزيرة الصناعية لانتاج الخرساته

71.77.10 A(\r.\/...) رقم الجهة المدنى: تاريخ السجل الصناعي: رقم السجل التجاري ٣٢٤٢٤٨ رقم السجل الصناعي ٣١٦٢

المنتج ا

المنتجات: -انتاج الخرسانة الجاهزة

 الموقع
 قسيمة
 الرقم الآلي
 مالك القسيمة

 منطقة
 قطعة
 قسيمة
 الرقم الآلي
 مالك القسيمة


 صليبية كبد
 B
 الهيئة العامة الصناعة

تاريخ التنفيذ: ٢٠٢-١٠-٢

ملاحظة : على المرخص له الالتزام بالشروط الواردة خلف هذا الترخيص .

مدير الادارة تعتبر هذه الرخصه نسخة الكترونية ولا تحتاج الى توقيع





## STATE OF KUWAIT INISTRY OF PUBLIC WORKS



## دولَه الكويت وزارة الأشغال العامَّة

11117

شهادة اعتماد

إنتاج الخرسانة الجاهزة

اسم الشركة / المصنع ::

مصنع الجزيرة الصناعية لإنتاج الخرسانة

الْعنوان : صليبية (كبد) قطعة ( B ) قسيمة ( 7 )

التلفون: 99940066

تاريخ الانتهاء 2024/2/5

تاريخ الإصدار 2023/8/6

#### وصف المواد المعتمدة:

• خرسانة جاهزة (خلط جاهز تتم أعمال الخلط داخل الخلاطات المركزية).

#### الاشتراطات:

- يجب سريان تراخيص المصنع والعجايرات الخاصة بالأجهزة المستخدمة بالخلط.
- المحافظة على تشوينات المواد المستخدمة في الخلط وطرق تخزينها ودرجة الحرارة ونسبة الرطوبة لتلك المواد .
  - يتم التقدم لمشاريع الوزارة من خلال المقاولين المعتمدين لتنفيذ المشاريع .
  - هذا الاعتماد لا يعفي المصنع من الفحوصات التي تنص عليها وثائق عقود المشاريع عند التوريد للمواقع.
    - لتزم المصنع بإغلاق مصب الخرسانة خلال سير سيارات الخلط الجاهز على الطرقات .
- الالت زام باست خدام نوعية الصلب وخ المعتمد (لايمستون إماراتي) بالخلطات التصميمية (K350(SRC),K300(OPC)) للمصنع طوال فترة الاعتماد .
  - a مراعاة التأكد من سلامة فحص التهدل (SLUMP) طبقاً ننوع الخلطة الخرسانية الموردة للموقع .
  - هذا الإعتماد ساري المفعول لمدة سنة أشهر (شريطة سريان تراخيص الشركة ) مع مراعاة تقديم طلب تجديد الإعتماد قبل شهرين من تاريخ انتهاء الشهادة.
    - في حالة المخالفة لأي من متطلبات الإعتماد المتفق عليها ، يعتبر الإعتماد لاغي ويحق للوزارة أخذ ما تراه مناسبا من الإجراءات القانونية .
    - الأنتزام بكتاب الهيئة العامة للبيئة بتاريخ (2022/11/22) بعدم وجود مخالفات بيئية محررة وفقاً لأحكام قانون حماية البيئة رقم ( 42 ) لسنة 2014 والمعدل بعض احكامة بالقانون رقم 99 لسنة 2015.
      - يحق لممثلي إدارة ضبط الجودة إضافة وتعديل شروط شهادة الاعتماد بما تراه مناسب لضبط جودة المنتج.

/ وكيل وزارة الأشغال العامة

م ريحان (المراجيرة وكيل وزارة مساعد قطاع المركز الحكومي للفحوصات المسط الحددة والأبحاث والتكارم



# اعتماد الخلطات التصميمية في وزارة الدفاع





الاشكارة: MOD 23020902 تاريخ النتيجة: 26/03/2023 رقم العقدد: AL-JAZERA INDUSTRIAL : تاريخ الطلب: 09/02/2023



#### CHECK OF CONCRETE MIX DESIGN

ASTM C94/C94M-12

BS EN 12390 -1,2/2000 , BS EN 12390-3/2009

TYPE OF MIX K-300 - OPC

SL/NO.	MATERIALS	UNITS	Net Weight in Full dry Condition
1	CEMENT (OPC)	Kg/m³	350
2	WASHED SAND	Kg/m³	730
3	AGGREGATE 20mm	Kg/m³	650
4	AGGREGATE 10mm	Kg/m³	450
5	FREE WATER	L/m³	187
6	ADMIXTURE	L/m³	4.5
REC	QUIRED SLUMP @ 60 Min.	cm	(18 ± 4 )
	ED COMPRESSIVE STRENGTH	(kgf/cm²)	K 300
	W/C RATIO		0.53

#### TEST RESULT:

CURING PERIOD		7	7 ( Days ) 28 ( Days		( Days	5)	
CUBE MARKED		R1	R2	R3	R4	R5	R6
COMPRESSIVE STRENGTH	Kg /cm²	365.6	385.5	351.7	448.7	449.7	463.1
AVERAGE (COMPRESSIVE STRENGTH)	Kg /cm²		367.6			453.8	
CASTING DATE			12/02/2023				
MIXING TIME	Min		de relier		5		
SLUMP TEST @ 60 minutes	cm			2	20		
CONCRETE TEMPERATURE	C.			2	22		

#### REMARKS:

MATERIALS	MATERIAL TYPE	SOURCE
CEMENT	OPC / SRC	ALGHANAEM INDUSTRIAL
SAND	WASHED SAND	AL-JAZEERA INDUSTRIAL CO.
AGGREGATE	LIMESTONE	AHGAR INTERNATIONAL
ADMIXTURE	EPOCON SP 545	BAXEL CONSTRUCTION MATERIAL

النئانج تمثل العينات المقدمة للقحص فقط

page 02 of 03

Teat reports shall not be reproduced except to full, without written approval of the laboratory



الإشـــارة: MOD 23020902 تاريخ النتيجة: 26/03/2023 رقم العقد: المتعهد: AL-JAZERA INDUSTRIAL تاريخ الطلب: 09/02/2023



## CHECK OF CONCRETE MIX DESIGN

ASTM C94/C94M-12

BS EN 12390 -1,2/2000 , BS EN 12390-3/2009

TYPE OF MIX K-350 - SRC

		UNITS	Net Weight in Full dry Condition
SL/NO.	MATERIALS		400
SLINU.	CEMENT (SRC)	Kg/m³	730
1	WASHED SAND	Kg/m³	650
2	AGGREGATE 20mm	Kg/m³	445
3	AGGREGATE 10mm	Kg/m³	
4	AGGREGATE 10mm	L/m³	184
5	FREE WATER	L/m³	6
6	ADMIXTURE		(18 ± 4 )
REC	QUIRED SLUMP @ 60 Min.	cm	K 350
REQUIR	ED COMPRESSIVE STRENGTH W/C RATIO	(kgf/cm²)	0.46

#### TEST RESULT :

TEST RESULT.		7	( Days	)	28	( Days	5)
CURING PERIOD		1	_		R4	R5	R6
CUBE MARKED		R1	R2	R3		A STATE OF THE PARTY OF THE PAR	550 6
COMPRESSIVE STRENGTH	Kg /cm²	446.4	468.2	456.8	543.4	511.0	550.0
AVERAGE (COMPRESSIVE STRENGTH)	Kg /cm²		457.1	40/00	12023	535.0	
CASTING DATE				12/02	/2023		
MIXING TIME	Min				0		
SLUMP TEST @ 60 minutes	cm				9	-	
CONCRETE TEMPERATURE	c.			2	2		-

#### REMARKS:

SOURCE	MATERIAL TYPE	MATERIALS
ALGHANAEM INDUSTRIAL	OPC / SRC	CEMENT
AL-JAZEERA INDUSTRIAL CO.	WASHED SAND	SAND
AHGAR INTERNATIONAL	LIMESTONE	AGGREGATE
BAXEL CONSTRUCTION MATERI	EPOCON SP 545	ADMIXTURE

النتائج تمثل العينات الملامة للقحص فلط

page 03 of 03

Test reports shall not be reproduced except in full, willout written approval of the laboratory Transfer III will jour written approval of the state of t

## معايرات المصنع

معايرة المحطة المركزية معايرة ماكينة تكسير المكتبات







#### **Ministry of Public Works** Govt. Center For Testing, Quality Control and Research قارة الأشغال العامة Construction Lab. Department



		Cal	ibration of Bate	ching Plant	E WINDLE
App. No.	288/2023			Date:	11/05/2023
Applicant Name	ج الخرسانة	الصناعية لإنتا	مصنع الجزيرة	Date on:	30/04/2023
<b>Full Admixture Scal</b>	e Capacity	50	KG	Date of Test:	08/05/2023
Location		کبد		Serial No.	GA929102
			and the second	Туре	Liebherr

Lab Weight (KG)	Admixture Scale (KG)	Error (KG)	% Error With Respect To	Limit
上京 理论 型版	THE RESIDENCE OF THE PARTY OF T	MINE IN	Scale ind. Load	<b>"你不是</b>
5	5	-		(-3,+3)
10	10		_	(-3,+3)
15	15			(-3,+3)
20	20	-		(-3,+3)
25	25			(-3,+3)
30	30			(-3,+3)
35	35			(-3,+3)
40	40			(-3,+3)
div = 0.02 KG			Full Sc	ale: 50 K

Remark: (1) This batching plant comply with ASTMC94/92 Requirements. This certificate is valid for a period of 6 months from the date of test provided no damage occures during this period.

(2) Scale division shall be equal to 0.1% of the nominal capacity.

(3/3)

Manager, of Const. Labs. Department

INCO - LABO (KSCC)

Paid up Capital K.D.1,350,000 (C.R. No. 65947)



شركة مختبرات إنكو الصناعية (ش.م.ك.م) رأس المال المدفوع ۱٬۳٥۰،۰۰۰ دك (س.ترقم ، ۲۵۹٤۷)

حاصل على الأيزو ٢٠١٧، ١٧٠٢٥

Accredited to ISO/IEC 17025: 2017

فحوصات المواد \* أبحاث التربة \* المساحة \* المعايرة \* التقييم الإنشائي \* فحوصات البيئة \* فحوصات الأوتاد Material Testing \* Soil Investigation \* Surveying \* Calibration \* Structural Evaluation \* Environmental Testing \* Piles Testing

#### CALIBRATION CERTIFICATE

Job Order No.: 23-3-158

Certificate No.: F/101/23

Issued Date: 30-Apr-23

#### Calibration Results

Indicated	Actual	The state of the s	Relative error	of	
Machine Force (Fi)	Reference Force (F)	Accuracy (q) (%)	Repeatability (b) (%)	Resolution (a) (%)	Expanded Uncertainty (± %)
400	400.055	0.0	0.1	0.0	0.7
700	698.778	0.2	0.1	0.0	0.7
1000	1000.264	0.0	0.1	0.0	0.7
1300	1302.349	-0.2	0.1	0.0	0.7
1600	1602.973	-0.2	0.0	0.0	0.7

The results concern only the objects specified in this certificate.


Relative zero error (f <sub>o</sub> ):	-0.01 %
The Lower Limit of the Range	400 kN
Class of the Machine :	north Thomas

#### Uncertainty of Measurement

The reported expanded uncertainty of measurement is stated as the standard uncertainty of measurement multiplied by the coverage factor k = 2, which for a normal distribution corresponds to a coverage probability of approximately 95 %. The standard uncertainty of measurement has been determined in accordance with A2LA requirements.

Calibrated by

Mr. Amer A. Karim Calibration Technician



This certificate shall not be reproduced except in full, without the written approval of the laboratory.

P.O.Box 21073 Safat 13071, Kuwait Tel.: +965 2471 0780 2475 2320


2475 2330 2471 6520 Fax: +965 2471 6526





TESTING CERT#2487.01 & 2487.02





س.ب: ۲۱۰۷۳ الصفاة ١٢٠٧١- الكويت تلفون: ۲٤٧١٠٧٨٠ ه١ TIVOTTT. YEVOYTT. TEVITAT.



#### Ministry of Public Works Govt. Center For Testing, Quality Control and Research قارة الأشغال العامة Construction Lab. Department



A== N		Cali	ibration of Bate	ching Plant	
App. No. Applicant Name	288/2023			Date:	11/05/2023
Full Microsilica Sca	اج الخرسانة		مصنع الجزيرة	Date on:	30/04/2023
Full Water Scale Ca	le Capacity	200	KG	Date of Test:	08/05/2023
Location	pacity	750	KG	Serial No.	GA929102
- Cotton		کبد		Туре	Liebherr

ab Weight (KG)	Microsilica Scale (KG)	Error (KG)	% Error With Respect To	Limit
20	。	學學學學	Scale ind. Load	200000
20	20	*	•	(3.12)
40	40			(-3,+3)
60	60		55%	(-3,+3)
80	80	-		(-3,+3)
100	56944	-		(-3,+3)
120	100			(-3,+3)
	120	•	n <b>⊎</b> o	(-3,+3)
140	140	X <b>=</b> .		
160	160			(-3,+3)
div = 0.2 KG				(-3,+3) ale : 200 l

Lab Weight (KG)	Water Scale (KG)	Error (KG)	% Error With Respect To	Limit
A SECTION OF SECTION O			Scale ind. Load	Cilling
75	75	-	-	(-3,+3)
150	150	1450-		
225	225			(-3,+3)
300	300			(-3,+3)
		-		(-3,+3)
375	375	-		(-3,+3)
450	450	-		(-3,+3)
525	525	-		(-3,+3)
600	600			(-3,+3)
div = 1 KG			Full Sa	ale: 750 K

Remark: (1) This batching plant comply with ASTMC94/92 Requirements. This certificate is valid for a period of 6 months from the date of test provided no damage occures during this period.

(2) Scale division shall be equal to 0.1% of the nominal capacity.

(2/3)



#### INCU - LABS (KSCC)

Pald up Capital K.D.1,350,000 (C.R. No. 65947)

Accredited to ISO/IEC 17025: 2017



شركة مختبرات إنكو الصناعية (ش.م.ك.م) رأس المال المدفوع ، ، ، ، ، ، ، ، دك (س.ترقم ، ١٥٩٤٧)

حاصل على الأيزو ١٧٠٢٥، ١٧٠٢٥

فحوصات المواد \* أبحاث التربة \* المساحة \* المعايرة \* التقييم الإنشائي \* فحوصات البيئة \* فحوصات الأوتاد Material Testing \* Soil Investigation \* Surveying \* Calibration \* Structural Evaluation \* Environmental Testing \* Piles Testing

#### CALIBRATION CERTIFICATE

Job Order No.: 23-3-158

Certificate No.: F/101/23

Issued Date: 30-Apr-23

**Customer Data** 

Company Name:

AL Jazeera Ready Mix

Address:

Kabd, Kuwait

**Device Under Calibration** 

Description:

Compression Machine

Manufacturer: Type/Model No.:

**U** Test UTC-4221

Serial No.: Code No.:

18/00/1690 NA

Receipt Date:

30-Apr-23 Calibration Date: 30-Apr-23

Due Date:

29-Apr-24

Range: Resolution: 2000 KN 0.1 kN

**Environmental Condition During Calibration** 

Start: End: Temperature 21.9 °C 22.2 °C

**Relative Humidity** 49.8 %

50.5 %

Pressure

NA NA

Reference Standard Used

Description

Manufacturer

Serial No.

Model No.

Traceability

Standard Load cell w/ Digitizer

AEP

542121

CLF 3MN

DAkkS/Germany


#### Calibration Method

The calibration was performed according to in-house method IC-F-CM-01 which is based on the method recommended in ISO 7500-1 using standard equipment traceable to SI units through National or International Standard.

#### Remarks

- 1. The attached results were obtained during the time of calibration and refer only to the particular instrument submitted.
- 2. Should the instrument be modified or damage in any way, or develop inconsistent readings, the results may not be valid and the unit will require recalibration.
- This calibration certificate is issued in accordance with the requirements of ISO/IEC 17025: 2017
- The calibration was performed on-site.

Reviewed By Eng. Ahmed Hany Calibration Engineer



Approved By

Eng. Gamal Abdel Aziz Head of Calibration Department

This certificate shall not be reproduced except in full, without the written approval of the laboratory.

P.O.Box 21073 Safat 13071, Kuwait Tel.: +965 2471 0780

Fax: +965 2471 6526

2475 2320 2475 2330 2471 6520





**ORGANIZATIONAL** MEMBER



ص.ب: ۲۱۰۷۳ الصفاة ١٣٠٧١- الكويت تلفون: ۲٤٧١٠٧٨٠ تلفون TIVOTTT. YEVAYPY. YEVITOY.

فاكس: ۲۲۰۲۱۷۱۲ ه۲۰+

ISO/IEC 17025:2017 TESTING CERT#2487 01 & 2487 02



#### Ministry of Public Works Govt. Center For Testing, **Quality Control and Research**



		Calil	oration of Bate	ching Plant		
- 20	288/2023			Date:	11/05/2023	
App. No.		مصنع الجزيرة الصناعية لإنتا		Date on:	30/04/2023	
Applicant Name	ج الخرسانة   Applicant Name		the selection of the se		08/05/2023	
<b>Full Aggregate Scal</b>	e Capacity	7500	KG	Date of Test:		
Full Cement Scale		1500	KG	Serial No.	GA929102	
Location		کید		Туре	Liebherr	

Lab Weight (KG)	Aggregate Scale (KG)	Error (KG)	% Error With R	espect To	Limit
Lab Weight (NO)	A STATE OF THE STA		Scale ind. Load	Full Scale	<b>科斯特斯</b>
750	750	(-	-	•	(-3,+3)
1500	1500	-		-	(-3,+3)
2250	2250	112			(-3,+3)
	3000	-	-	-	(-1,+1)
3000 3750	3750	-		-	(-1,+1)
4500	4500	-		-	(-1,+1)
	5250	7-		-	(-1,+1)
5250	6000	-	4	-	(-1,+1)
6000 1 div = 10 KG	0000			Full Sca	e :7500 KG

Lab Weight (KG)	Cement Scale (KG)	Error (KG)	% Error With Respect To	Limit
arginal makes a	to the second of the second	<b>电影电影</b>	Scale ind. Load	The second
150	150			(0,+4)
300	300	-	•	(0,+4)
450	450	NEAS COM	AFFECT THE NAME OF	(0,+4)
600	600			(-1,+1)
750	750			(-1,+1)
900	900			(-1,+1)
1050	1050	- 0.0		(-1,+1)
1200	1200			(-1,+1)
div = 2 KG			Full Scale	: 1500 K

Remark: (1) This batching plant comply with ASTMC94/92 Requirements. This certificate is valid for a period of 6 months from the date of test provided no damage occures during this period.

(2) Scale division shall be equal to 0.1% of the nominal capacity.

(1/3)

Manager, of Const. Labs. 1

# اعتمادات موردين المواد الأولية في وزارة الأشغال

# اعتمادات مورد الأسمنت و وزارة الاشغال و وزارة الدفاع



#### STATE OF KUWAIT MINISTRY OF DEFENCE MILITARY ENGINEERING PROJECTS



تقر<u>ب</u>ر فد ص Test Report

Scrial Number QC 74210130323 رقسيهم الإشسارة **Date of Reporting** 09/03/2023 تاريـــخ التقريــ Contractor/Client شركة الغنائم ( اسمئت طارق ) المتعهد / العميسل Project Address الشعبة الصناعية موقسيح المشسروع Supervision Site ضبط الجودة جهيسة الإنسراف اسمنت عادي Type I Description & Identification / وصف/ تمييسز العينسة/حالة Condition of Sample(s) **Date of Test Request** تاريــــخ الطل 06/02/2023

مراقب المختبرات

Test reports shall not reproduced except in full, without written approval of the laboratory.



## STATE OF KUWAIT MINISTRY OF DEFENCE

MILITARY ENGINEERING PROJECTS

272740000480 2023/04/03



## 

المحترمين

السادة / شركة الغنائم الصناعية (أسمنت طارق) تحية طبية ويعد ،،،

الموضوع: تجديد اعتماد منتجات شركة الغنائم الصناعية السمنت طارق) الإسمنت البورتلادي العادي Type I و الإسمنت البورتلادي المقاوم للكبريتات Type V

بالإشارة إلى الموضوع أعسلاه ، و إلى كتابكم وارد هندسة المنشأت المسكرية رقم الا 8148 بنازيم 2022/12/20 (مرفق صورة) نحيطكم علماً بأنه قد تدريارة المدن والتدقيق على المستندات و خطوط الإنتاج وتم سحب عينات من منتجات المصنع للتأكد مطابقتها المواصدات القياسيسة ASTM و ذلك لكل من الآتي:-

- 1. الإسمنت البورت الندي العادي 1
- 2 الإسمنت البورتسلاندي المقاوم للكبريتات Type V

و عليه فإنه لا ماتع لدينا من تجديد الاعتماد لمنشجات مصنعكم اعلاه وذلك بحسب الاشتراطات الواردة بشهادة الاعتماد رقم 01-270323 أ

لا \_\_راءاتكم ،،،

وتفضلوا بقبول فانق الشكر ،،،

تسخة : 74200

وكيال الوزارة وكياد وكيال السوزارة المساعد وكيال المنشآت المسكرية بالتكليف عيامار محمد ناصر النسيام



## STATE OF KUWAIT MINISTRY OF PUBLIC WORKS



## دولَه الكويت وزارة الأشغال العامة

CIALIV

C.C1-10-C1

شهادة اعتماد مواد إنشائية

أسمينت مقاوم للأملاح ( TYPE V )

اسم الشركة / المصنع:

شركة الغنائم الصناعية ش.م.ك (مقفلة)

العنوان:

الشعيبة الصناعية ت: 22258360 - ص.ب : 2118 الصفاة 13022 الكويت

تاريخ الإصدار \_\_\_\_ ت

2021 / 12 / 16

تاريخ الانتهاء 2023 / 12 / 15

#### وصف المواد المعتمدة :

أسمنت مقاوم للأملاح ( TYPE V ) / (أسمنت طارق).

من إنتاج شركة الغائم الصناعية - الكويت .

#### الإشتراطات:

- ضرورة الالتزام بالمواصفات العامة للوزارة والمواصفات الخاصة لكل مشروع على حده والمتعلقة بهذه المنتجات.
- يتم التقدم بهذه المنتجات من خلال المقاولين المعتمدين المشاريع العائدة لوزارة الأشغال العامة شريطة أن تطابق المواصفات العامة للوزارة و المواصفات الخاصة بالعقد الذي يرغب في استخدام هذه المنتجات.
  - ضرورة الالتزام بالمادة رقم 62 من قانون الجهاز المركزي للمناقصات رقم 49 نعام 2016 والمتعلقة بأفضلية المنتجات الوطنية والمنتجات ذات المنشأ الوطني حسب النظم واللوائح المتبعة.
    - هذا الاعتماد لا يعفي هذه المنتجات من إجراء الفحوصات اللازمة والدورية عند التوريد لأي مشروع.
    - يحق للوزارة المرور والكشف على المنتج أعلاه للتأكد من جودة المنتج ومطابقته للمواصفات في أي وقت خلال فترة سربان شهادة الإعتماد.
  - هذا الإعتماد ساري المفعول لمدة سنتين ( شريطة سريان تراخيص الشركة ) مع مراعاة تقديم طلب تجديد الإعتماد قبل شهرين من تاريخ انتهاء الشهادة.
    - في حالة المخالفة لأي من منطلبات الإعتماد المنفق عليها يعتبر الإعتماد لاغي وبحق للوزارة أخذ ما تراه مناسباً من الإجراءات القانونية.
  - الإلتزام بكتاب الهيلة العامة للبيئة رقم ( ه.ع.ب. إم.ع.ب. إم.ع)6382) بتاريخ (2021/11/29) بعدم وجود مخالفات بيئية محددة وقفاً لأحكام قانون حماية البيلة
     رقم ( 42 ) لسنة 2014 والمحل بعض أحكامه بالقانون رقم ( 99 ) لسنة 2015.

وكيل وزارة الأشغال العامة لهندس/ عبد الحرار المالد العنزي الموضيال الماليات مطاع الركز المحكوم المنطوصات



# اعتماد مصدر الصلبوخ -احجارانترناشونال مع مع فحوصات وزارة الاشغال (كيميائي+ فيزيائي)





Ministry of Public Works
Govt. Center For Testing Quality Control and
Research
Cons. Lab. Department
SABHAN - Kuwait



Application No.:

1383 /2022-B

وزارة الاشغال العامة / ادارة ضبط الجودة : Name Of Ministry شركة احجار انترناشونال :Contract NO & Contractor

Description of Sample: Aggregate 1/2 "

Date: 31/8/2022 Data ON: 2/8/2022 Date of Test: 30/8/2022

Lab No : 414/2022

#### **Test Of Aggregate**

#### Results:

No.	Type of Test	Results	Test Specification
1	The water soluble Chloride (Cl )	0.0076 %	B.S. 812 PART 117
2	The total sulphate (acid soluble) as (SO <sub>3</sub> )	0.062 %	B.S. 812 PART 118
3	Potential Reactivity	This Sample Of Aggregate is Chemically Innocuous	ASTM C 289/94
4	Moisture content	0.18	ASTM C 566
5	Loss on ignition	1.70	ASTM C 114
6	Organic Impurities	The Color of the supernatant liquid above the test sample was found to be Lighter than that of reference standard solution. Therefore there is no injurious organic compound in the sample.	ASTM C 40/92
7	Coal and lignite Content	No light weight pieces were found to be floating on the liquid. Therefore, coal and lignite are absent.	ASTM C-123

Remarks:-1. Results represent sample submitted for test only.

Manager of Const Labs. Department

V.R





Ministry of Public Works Govt. Center For Testing Quality Control and Research Cons. Lab. Department SABHAN - Kuwait



Application No.:

1384/2022-B

وزارة الاشغال العامة/ ادارة ضبط الجودة: Name Of Ministry شركة احجار انترناشونال: Contract NO. & Contractor

Description of Sample: Aggregate  $^3/_8$  "

Date: 24/8/2022 Data ON: 2/8/2022

Date of Test: 22/8/2022

Lab No: 415/2022

#### **Test Of Aggregate**

#### Results:

No.	Type of Test	Results	Test Specification
1	The water soluble Chloride (Cl )	0.0053 %	B.S. 812 PART 117
2	The total sulphate (acid soluble) (SO <sub>3</sub> )	0.059 %	B.S. 812 PART 118
3	Potential Reactivity	The Sample Of Aggregate is Chemically innocuous	ASTM C 289/94
4	Moisture content	0.11 %	ASTM C 566
5	Loss on ignition	42.58 %	ASTM C 114
6	Organic impurities	The Color of the supernatant liquid above the test sample was found to be Lighter than that of reference standard solution. Therefore there is no injurious organic compound in the sample.	ASTM C 40/92
7	Coal and lignite Content	No light weight pieces were found to be floating on the liquid. Therefore, coal and lignite are absent.	ASTM C-123

Remarks:-1. Results represent sample submitted for test only.

Manager of Const Labs. Department

فكدير إدارة مختبرات الإنشاءات

V.R





Ministry of Public Works
Govt. Center For Testing Quality Control and
Research
Cons. Lab. Department
SABHAN - Kuwait



Application No.:

1382 /2022-B

وزارة الاشغال العامة ادارة ضبط الجودة: Name Of Ministry

Applicant's Name: شرکة احجار اِنترناشونال Description of Sample: Aggregate  $^3/_4$  " Date: 28/9/2022 Data ON: 2/8/2022

Date of Test: 26/9/2022

Lab No: 413/2022

#### **Test Of Aggregate**

#### Results:

No.	Type of Test	Results	Test Specification
1	The water soluble Chloride (Cl )	0.0035 %	B.S. 812 PART 117
2	The total sulphate (acid soluble) as (SO <sub>3</sub> )	0.025 %	B.S. 812 PART 118
3	Potential Reactivity	This Sample Of Aggregate is Chemically Innocuous	ASTM C 289/94
4	Moisture content	0.09	ASTM C 566
5	Loss on ignition	47.38	ASTM C 114
6	Organic Impurities	The Color of the supernatant liquid above the test sample was found to be Lighter than that of reference standard solution. Therefore there is no injurious organic compound in the sample.	ASTM C 40/92
7	Coal and lignite Content	No light weight pieces were found to be floating on the liquid . Therefore , coal and lignite are absent.	ASTM C-123

Remarks:-1. Results represent sample submitted for test only

Manager of Const Labs. Department

Ve 3





Ministry of Public Works Govt. Center For Testing Quality Control and Research Construction Lab. Department



وزارة الأشغـال العـامـة MINISTRY OF PUBLIC WORKS

CONSTRUCTION Lab. Departmen

	TEST OF COARSE AGGREGA AS PER B.S. 882/92 & ASTM C	and the same of th			
App. No.	1382/2022	Date:	04/09/2022		
Applicant	Date On: 02/08/2022 وزارة الأشغال العامة _ إدارة ضبط الجودة				
Contract	شركة احجار انترناشونال		-1		
Description of Sample (as applicant's claim)	AGGREGATE 3/4" (20 mm)				

1a- Sieve Analysis (by weight) According to B.S. 812 SEC. 103.1/01:

B.S. SIEVE	% RETAINED ON EACH SIEVE	% PASSING EACH SIEVE	B.S. 882/92 LIMITS
37.5mm	NiL	100	100
20mm	6.98	93.02	85 – 100
14 mm	83.32	9.70	0 – 70
10 mm	9.04	0.66	0 – 25
5 mm	0.20	0.46	0-5
Pan	0.46	0.00	<u></u>

No.	Type of test	Result	Specification limits	Test specification	
1b	% by mass passing 75 μm sieve	0.40 %	4 % max. as per B.S. 882/92	B.S. 812 SEC. 103.1/85	
2	Particles density (SSD)	2.66 Mg/m <sup>3</sup>	-	B.S. 812 P.T. 2/95	
3	Water absorption	0.62 %	i <del>T</del> ei	B.S. 812 P.T. 2/95	
4	Bulk density	1.64 Mg/m <sup>3</sup>		B.S. 812 P.T. 2/95	
5	% voids	38.34 %		B.S. 812 P.T. 2/95	
6	% clay lumps & friable particules	0.26	(2-10)% max according to type of concrete as per ASTM C33/11	ASTM C142/10	
7	Fineness modulus	2.16	-	ASTM C136/14	
8	Impact value (dry)	mpact value (dry) 11.39 % (25 - 45) % max. concrete as per a		B.S. 812 P.T. 112/90	
9	Crushing value	19.50 %	-	B.S. 812 P.T. 110/90	
10			(50, 100, 150) KN min according to type of concrete as per BS 882/92	BS 812 PT.111/90	
11	Los angeles	24.78 %	50 % max as per ASTM C 33/11	ASTM C 131/14	
12	Flakiness index	14.93 %	40 % max. for crushed agg. as per B.S. 882/92	B.S. 812 S.E.C. 105.2/89	
13	Elongation index	14.21 %		B.S. 812 S.E.C. 105.2/90	
14a	Shell content for agg .Finer than 10 mm	NIL	20% max as per BS 882/92	BS 812 PT. 106/85	
14b	shell content for agg Coarser than 10 mm	NIL	8% max as per BS 882/92		
15	Soundness ( using sodium sulphate – 5cycles )	0.72%	12% max as per ASTM C-33/11	ASTM C-88/13	

#### Remarks:

- 1- Regarding Above Tests Results, Sample Complies With BS 882/92 & ASTM C 33/11 LIMITS.
- 2- Results Represent Sample Submitted For Test Only.
- 3- The Uncertainty Of Balance For Coarse Agg. Is ± 1.07gm for 3/4 inch.
- 4- The Applicant claims that, the Aggregate is Limestone.

MANAGER, CONST LABS DEPARTMENT

المعزين/ (فرافي في المالة) مدين إذارة مختيان الإنتاءات





Ministry of Public Works Govt. Center For Testing Quality Control and Research



MINISTRY OF PUBLIC WORKS

Construction Lab. Department

NEWKUWAII	MINISTRY OF PUBLIC WORKS	I.	
	TEST OF COARSE AGGREG		
	AS PER B.S. 882/92 & ASTM	C 33/11	
App. No.	2445/2021	Date:	23/03/2022
Applicant	شركة أحجار انترناشيونال للصلبوخ	Date On:	27/12/2021
Description of Sample (as applicant's claim)	AGGREGATE 1/2" (14 mm)		

1a- Sieve Analysis (by weight) According to B.S. 812 SEC. 103.1/01:

B.S. SIEVE	% RETAINED ON EACH SIEVE	% PASSING EACH SIEVE	B.S. 882/92 LIMITS
20 mm	NIL	100	100
14 mm	NIL	100	85 – 100
10 mm	66.20	33.80	0 – 50
5 mm	33.20	0.60	0 – 10
Pan	0.60	0.00	-

No.	Type of test	Result	Specification limits	Test specification
1b	% by mass passing 75 μm sieve	0.40 %	4 % max. as per B.S. 882/92	B.S. 812 SEC. 103.1/85
2	Particles density (SSD)	2.7 Mg/m <sup>3</sup>	-	B.S. 812 P.T. 2/95
3	Water absorption	0.50 %		B.S. 812 P.T. 2/95
4	Bulk density	1.6 Mg/m3		B.S. 812 P.T. 2/95
5	% voids	38.59 %	-	B.S. 812 P.T. 2/95
6	% clay lumps & friable particules	0.4 %	(2-10)% max according to type of concrete as per ASTM C33/11	ASTM C142/10
7	Fineness modulus	1.8	W	ASTM C136/14
8	Impact value (dry)	14.97 %	(25 – 45) % max. acc. to type of concrete as per as B.S 882/92	B.S. 812 P.T. 112/90
9	Crushing value	20.24 %		B.S. 812 P.T. 110/90
10	10% fines value (dry )	222 KN	(50, 100, 150) KN min according to type of concrete as per BS 882/92	BS 812 PT.111/90
11	Los angeles	22.38 %	50 % max as per ASTM C 33/11	ASTM C 131/14
12	Flakiness index	19.62 %	40 % max. for crushed agg. as per B.S. 882/92	B.S. 812 S.E.C. 105.2/89
13	Elongation index	24.91 %	(4)	B.S. 812 S.E.C. 105.2/90

## · Remarks:

- 1- Regarding Above Tests Results, Sample Complies With BS 882/92 & ASTM C 33/11 LIMITS.
- 2- Results Represent Sample Submitted For Test Only.
- 3- The Uncertainty Of Balance For Coarse Agg. Is  $\pm$  0.764 gm for 1/2 inch.
- 4- The Applicant claims that, the Aggregate is Limestone.

MANAGER, CONST LABS DEPARTMENT







Ministry of Public Works Govt. Center For Testing Quality Control and Research Construction Lab. Department



	TEST OF COARSE AGGREGA AS PER B.S. 882/92 & ASTM C		
App. No.	1384/2022	Date:	29/08/2022
Applicant	وزارة الأشغال العامة - إدارة ضبط الجودة	Date On:	02/08/2022
Contract	شركة أحجار إنترناشونال		
Description of Sample (as applicant's claim)	AGGREGATE 3/8" ( 10mm )		

	1a- Sieve Ar	nalysis (by we	ight) According	to B.S.	812 SEC. 103.1/01:	
В	.S. SIEVE	% RETAIN	ED ON EACH S	IEVE	% PASSING EACH SIEVE	B.S. 882/92 LIMITS
	14 mm		NiL		100	100
	10 mm		0.70		99.30	85 – 100
	5 mm		94.40		4.90	0 – 25
9	2.36 mm		4.40	E 1 2 1	0.50	0-5
	Pan		0.50		0.00	-
No.	Туре	of test	Result		Specification limits	Test specification
1b	% by mass posieve	assing 75 µm	0.50 %	***************************************		B.S. 812 SEC. 103.1/85
2	Particles den	sity (SSD)	2.65 Mg/m <sup>3</sup>		-	B.S. 812 P.T. 2/95
3	Water absorp	otion	0.60 %		- B.S. 812 P.T. 2	
4	Bulk density		1.6 Mg/m <sup>3</sup>		(40)	B.S. 812 P.T. 2/95
5	% voids		39.62 %			B.S. 812 P.T. 2/95
6	% clay lumps & friable particules		0.21 %	(2-10)% max according to type of concrete as per ASTM C33/11		ASTM C142/10
7	Fineness mod	lulus	2.0			ASTM C136/14
8	Impact value	(dry)	14.93 %	(25 – 45) % max. acc. to type of concrete as per as B.S 882/92		B.S. 812 P.T. 112/90
9	Crushing valu	ie	17.41 %			B.S. 812 P.T. 110/90
10	10% fines va	lue (dry )	52.60 KN		100, 150) KN min according to of concrete as per BS 882/92	BS 812 PT.111/90
11	Los angeles		18.18%		6 max as per ASTM C 33/11	ASTM C 131/14
12	Flakiness ind	ex	22.57 %	40 % max for crushed agg as per		B.S. 812 S.E.C. 105.2/89
13	Elongation in		16.73 %		-	B.S. 812 S.E.C. 105.2/90
14a	Shell content .Finer than 10		NIL	2	20% max as per BS 882/92	
14b	shell content Coarser than		NIL		8% max as per BS 882/92	BS 812 PT. 106/85
15	Soundness ( u sulphate – 5cy		0.4 %	12%	6 max as per ASTM C-33/11	ASTM C-88/13

## Remarks:

- 1- Regarding Above Tests Results, Sample Complies With BS 882/92 & ASTM C 33/11 LIMITS.
- 2- Results Represent Sample Submitted For Test Only.
- 3- The Uncertainty Of Balance For Coarse Agg. Is ± 0.629gm for 3/8 inch.
- 4- The Applicant claims that, the Aggregate is Limestone.

# STATE OF KUWAIT MINISTRY OF PUBLIC WORKS



# دولُسة الكويت وَزَارة الأشغال العامنة

VIV37

شـهــادة اعتمــاد مخازن صلبوخ

صلبوخ إماراتسي لايمستون

اسم الشركة / المصنع:

شركة الأحجار انترناشيونال لاستيراد الصلبوخ.

العنوان:

ميناء عبدالله قطعة (1) قسيمة (24-23)

2 فاكس: 24824017

تلغون: 24824016

فاكس: 24824017

تلفون: 24824016

الرمز البريدي: 13025 - الكويت

ص.ب: 2485 - الصفاة

تاريخ الانتهاء

2023/8/12

تاريخ الإصدار

2023/2/13

## وصف المواد المعتمدة:

صلبوخ اليمستون للأحجام ("3/8" - "3/4" - "1/2") للاستخدام في أعمال الخرساته الجاهرة والمنتجات الخرسانية المختلفة. من انتاج كسارات احجار رأس الخيمة (RAK ROCK)( الإمارات العربية المتحدة ) لصالح شركة الأحجار انترناشيونال المستيراد الصلبوخ (الكويت).

- يُتم التقدم بهذه المنتجات أعلاه من خلال المقاولين المعتمدين لمشاريع وزارة الأشغال العامة التي يطلب منها استخدام هذه المنتجات شريطة أن تطابق هذه المنتجات العامة لوزارة الأشغال والمواصفات الخاصة للعقد الذي يرغب في استخدام هذا المنتجات.

- ضرورة الالتزام بالمادة رقم 62 من قانون الجهاز المركزي للمناقصات رقم 49 لعام 2016 والمتعلقة بافضلية المنتجات الوطنية والمنتجات ذات المنشأ الوطني حسب النظم واللوائح المتبعة.

المنت الوطني حصب النظم والنوائح المعبعة. - يحق لممثلي الوزارة (قطاع المركز الحكومي) سحب العينات من أماكن التشوين وكذلك التأكد من جودة الصلبوخ المورد بشكل دوري الي مصاقع انتاج الخرسانة أو المنتجات الخرسانية والمرور والكشف على المنتجات أعلاه للتأكد من جودة المنتجات ومطابقتها للمواصفات في أي وقت خلال فنرة سريان شهادة الاعتماد.

- الالتزام بعدم تشوين صلبوخ غير معتمد من قبل وزارة الأشفال العامة.

- هذا الاعتماد لا يعفي هذه المنتجات من إجراء الفحوصات اللزمة والدورية عند التوريد لأي عقد.

ـ هذا الاعتماد ساري المفعول لمدة ستة أشهر (شريطة سريان تراخيص الشركة) مع مراعاة تقديم طلب تجديد الاعتماد قبل شهرين من تاريخ انتهاء الشهادة.

- في حالة المخالفة لأي من متطلبات الاعتماد المتفق عليها يعتبر الاعتماد لاغي ويحق للوزارة أخذ ما تراه مناسباً من الإجراءات القتونية.

- هذا الإعتماد خاص للإستخدام في أعمال الخرسانة الجاهزة والمنتجات الخرسانية المختلفة وفي حال استخدامها في مجالات أخرى يجب اعتماد الصلبوخ من الجهة المختصة .

- في حلة تغيير بلد المنشأ ( الإمارات العربية المتحدة ) يعتبر هذا الاعتماد لاغياً.

- الألتزام بكتاب الهيئة العامة للبيئة) بتاريخ 2022/11/10 بعدم وجود مخالفات بيئية محررة وفقاً لأحكام قاتون حماية البيئة رقم ( 42 ) لسنة 2014 والمعدل بعض احكامه بالقاتون رقم 99 لسنة 2015.

ر وكيل وزارة الأشغال العامة

حُرِينَ الْمُحْرِينَ وَالْمُوارِةُ مِساعِد

وكيل وزاره مساعد قطاع المركز الحمكومي للفحوصات وضبط الجودة والأبحاث بالتكليف



# STATE OF KUWAIT UNISTRY OF PUBLIC WORKS



# دولَسة الكسويَست وَزارة الأشغال العامَّة

C19/11 C.C1-10-C1

شهادة اعتماد مواد إنشائية

أسمسنت مقاوم للأملاح ( TYPE V )

اسم الشركة / المصنع:

شركة الغنائم الصناعية ش.م.ك (مقفلة)

العنوان :

الشعيبة الصناعية ت: 22258360 - ص.ب : 2118 الصفاة 13022 الكويت

تاريخ الانتهاء 2023 | 12 | 2023

SPEC

تاريخ الإصدار 16 / 12 / 2021

## وصف المواد المعتمدة:

اسمنت مقاوم للأملاح ( TYPE V ) / (اسمنت طارق).

من إنتاج شركة الغالم الصناعية - الكويت .

## الاشتراطات:

- ضرورة الالترام بالمواصفات العامة للوزارة والمواصفات الخاصة لكل مشروع على حده والمتعلقة بهذه المنتجات.
- يتم التقدم بهذه المنتجات من خلال المقاولين المعتمدين للمشاريع العائدة لوزارة الأشغال العامة شريطة أن تطابق المواصفات العامة للوزارة و المواصفات الخاصة بالعقد الذي يرغب في استخدام هذه المنتجات.
  - ضرورة الالتزام بالمادة رقم 62 من قانون الجهاز المركزي للمناقصات رقم 49 لعام 2016 والمتعلقة بأفضلية المنتجات الوطنية والمنتجات ذات المنشأ
     الوطني حسب النظم واللواتح المتبعة.
    - هذا الاعتماد لا يعلي هذه المنتجات من إجراء الفحوصات اللازمة والدورية عند التوريد المي مشروع.
    - يحق للوزارة المرور والكشف على المنتج أعلاه للتأكد من جودة المنتج ومطابقته المواصفات في أي وقت خلال فترة مريان شهادة الإعتماد.
  - هذا الإعتماد ساري المفعول لمدة سنتين (شريطة سريان تراخيص الشركة ) مع مراعاة تقديم طلب تجديد الإعتماد قبل شهرين من تاريخ انتهاء الشهادة.
    - في حالة المخالفة لأي من متطلبات الإعتماد المتفق عليها يعتبر الإعتماد لاغي ويحق للوزارة أخذ ما تراه مناسباً من الإجراءات القاتونية.
  - الإلتزام بكتاب الهيلة العامة للبيلة رقم ( ه.ع.ب./م.ع/6382) بتاريخ (2021/11/29) بعدم وجود مخالفات بيئية محددة وفقاً لأحكام فانون حماية البيئة رقم ( 42 ) لسنة 2014 والمحل بعض أحكامه بالقانون رقم ( 99 ) لسنة 2015.

وعيل وزارة الأشغال العامة المهندس/ عبد المسلم خالد العنزي الموكيل المركز العكوم المنطوسات وضبط الجودة والاجواث



# اعتماد مصدر المادة المضافة في وزارة الأشغال

• فحوصات (كيميائي+ فيزيائي)

# STATE OF KUWAIT MINISTRY OF PUBLIC WORKS



## ُ دُولَــة الكــويَـت وَذَارة الأشغال العاميَّة

17/17

شهسادة اعتماد مواد إنشائية

117177.7

مادة مضافة للخرسانة (Admixture)

اسم الشركة / المصنع:

شركة ايبو الخليج للمواد للمواد الخصوصية (ش.م.ك.م)

العنوان:

ت: 22272555 ص. ب: 12017 - الشامية الرمز البريدي: 71651 - الكويت أمغرة الصناعية - قطعة: 4 - قسيمة: 279 - الرقم الآلي: 19018972

تاريخ الانتهاء

2025 / 01 / 30

تاريخ الإصدار

2023 / 01 / 30

وصف المواد المعتمدة:

- EPOCON SP 545: High Performance, High Water Reducing, Super Plasticizer Concrete
  Admixture.
- EPOCON SP 975: High Range Water Reducing Super Plasticizer Concrete Admixture.
  - مادة مضافة للخرسانة محلية الصنع من إنتاج شركة ايبو الخليج للمواد الخصوصية.

## الاشتراطات:

- ضرورة الإلتزام والتقيد بالمواصفات العامة للوزارة والمواصفات الخاصة ومتطلبات المواصفة الامريكية (ASTM C 494) وما يطرأ عليها من تعديلات لكل مشروع على حده والمتعلقة بهذه المنتجات.
  - يتم التقدم بهذه المنتجات من خلال المقاولين المعتمدين للمشاريع العائدة لوزارة الأشغال العامة شريطة أن تطابق المواصفات العامة للوزارة والمواصفات الخاصة بالعقد الذي يرغب في استخدام هذه المنتجات.
    - هذا الاعتماد لا يعفي هذه المنتجات من إجراء الفحوصات اللازمة عند التوريد لمشاريع الوزارة للتأكد من مطابقتها لمتطلبات المواصفات الفنية.
  - ضرورة الإلتزام بالمادة رقم 62 من قانون الجهاز المركزي للمناقصات رقم 49 لعام 2016 والمتعلقة الفضلية المنتجات الوطنية ذات المنشأ الوطني
     حسب النظم واللوائح المتبعة.
    - في حالة المخالفة لاي من متطلبات الاعتماد المتفق عليها يعتبر الاعتماد لاغي ويحق للوزارة أخذ ما تراه مناسبا من الإجراءات القانونية.
    - يحق للوزارة المرور والكشف على المنتج أعلاه للتأكد من جودة المنتج ومطابقته للمواصفات في أي وقت خلال فترة سريان شهادة الإعتماد.
      - هذا الإعتماد ساري المفعول لمدة سنتين مع مراعاة تقديم طلب تجديد الإعتماد قبل شهرين من تاريخ انتهاء الشهادة.
- الإلتزام بكتاب الهيئة العامة للبيئة رقم (ه.ع.ب/م.ع/3459) بتاريخ (2021/07/27) بعدم وجود مخالفات بيئية محددة وفقا لأحكام قانون حماية البيئة رقم (42) لمنة 2014 والمعدل بعض أحكامه بالقانون رقم (99) لمنة 2015.

وكيل وزارة الانخال العامة سرور معيض المعيي وكيل الوزارة المساعد لقطاع المشاريع الإنشائية بالتكليف







Ministry of Public works Govt. Center For Testing Quality and Research Cons. Lab. Department SABHAN-KUWAIT



Application No.: Applicant's Name: 1868/2021-B

شركة ايبو الخليج للمواد الخصوصية

**EPO GULF SPECIALTIES (K.S.C.C)** 

Description of Sample:

**EPOCON SP 545** 

Method of testing:

B.S 5075/TypeG

Date:

28/10/2021

Date ON:

13/10/2021

Date of Test: 24/10/2021

Test on: Chemical Admixture Uniformity

Test Results:

4		Characteristic	Result
	1	Chloride	0.00026%

Remarks: - Results represent only the sample submitted for test.

MANAGER OF CONST.LABS DEPARTMENT

### **CHARACTERISTICS**

EPOCON SP 545 is used for ready mix concrete and precast industry where high early compressive strength of the concrete is very important. It reduces mixing water (w/c ratio in concrete structure).It promotes excellent dispersion of the particles in cement resulting in a major improvement of the workability. It provides good wetting of fine-coarse aggregates, cement and mineral additives. It can be used under all weather conditions. It does not cause segregation. Free of Chloride ions. It can be used with all types of cement. Prolongation of workability time depends on cement type and ambient temperature

### **APPLICATIONS**

EPOCON SP 545 is used for cross-sections, readymix concrete for early mold in projects and all types of concrete structures. It is used for producing prefabricated members, economical concrete. quality plasticizer concrete, and precast industry. It is used for providing stabile concrete strength. It is used for increasing 16 hours and 28 days strength.

### **USAGE**

EPOCON SP 545 is used as a super plasticizer without any risks of segregation, for ready mix concrete where high workability is required. Concrete will be workable up to 3 hours if right dosage and mix design used. Mix cement (and pozzolanic materials), sand, aggregate and 50-70% of mixing water are mixed until a homogeneous mixture obtained. **EPOCON SP 545** is added the remaining mixing water and mixed until a homogeneous mixture and the desired workability obtained.

### **COMPATIBILITY**

EPOCON SP 545 can be used in all types of Portland cement, sulfate resisting cement and supplementary cementitious materials. EPOCON SP 545 should be dispensed directly into the mixer and should not be pre- mixed with other admixtures.

If other admixtures are to be used in concrete containing EPOCON SP 545, they must be dispensed separately.

## **TECHNICAL SPECIFICATION**

Test Name	Average Result
Chemical Composition	Sulfonated naphthalene based
Form	Liquid (Homogeneous)
Colour	Brown
Specific Gravity	1.210 ± 0.01 (20°C)
рН	7 ± 1.5
Chloride content%	< 0.06
Freeze harm	Complete Stir or agitate the container before use
Freeze temperature	0°C
Boiling point	100°C
Odor	Mild odor
Toxicity	None
Flammability	None
Clean-up	Water
Fumes during treatment	Slight
Environmental Hazards	None
Air Entrainment	Up to 2.0% depending on dosage rate and concrete proportioning.













10000 SP 54;





Ministry of Public Works Govt. Center For Testing, Quality Control and Research Construction Lab. Department



## TEST OF CONCRETE ADMIXTURE AS PER. ASTM C494/C494M-16

 APP.No
 : 1868/2021
 Date
 : 28/11/2021

 Applicant : شركة ايبو الخليج للمواد الخصوصية
 Date on : 13/10/2021

Contract : ---

DESCRIPTION OF MATERIAL: EPOCON SP 545 [Type-G]

SL. NO.	PROPERTIES	UNITS	CONTROL MIX.	TEST MIX.	SPECIFICATION LIMITS.
1	W/C	%	0.64	0.45	
2	Dosage as per Catalogue	Liter/m³	- 1	3.1	
3	Water Content	Liter/m³	196	137	
4	Water percentage to control	%	100 *	70	88%Max
5	aggregate content (34, 1/2, 3/8, 3/16) inch	Kg/m³	291	291	
6	Sand content	Kg/m³	677	677	
7	Cement content	Kg/m³	307	307	
8	Slump Test AS Per ASTM C 143/10a.	cm	8.0	10.0	9.0±1.5
	<b>COMPRESSIVE STRENGTH Test AS Per</b>	BS 1881 Part	.116/83	•	
9	3 DAYS	Kgf/cm <sup>2</sup>	178	312	
9	7 DAYS	Kgf/cm <sup>2</sup>	245	386	
	28 DAYS	Kgf/cm <sup>2</sup>	306	420	
	COMPRESSIVE STRENGTH PERCENTAGE	E TO CONTI	ROL	**	
10	3 DAYS	%	100	175	125 Min
10	7 DAYS	%	100	157	115 Min
	28 DAYS	%	100	137	110 Min
11	TEMPERATURE	C°	23	23	
12	AIR CONTENT Test AS PER ASTM C 23	1-10a		*	
	Air Content	%	1.2	2.2	*

## Remarks:

- \* The air content of both the mixture containing the admixture under test and the reference concrete mixture shall be 3.5% or less, and the difference between the air contents of the two mixtures shall not exceed 1.0.
- 1- Regarding above tests results, the submitted sample **complies** with requirements of ASTM C494/C494M-16.
- 2- The applicant claims that; the tested admixture is EPOCON SP 545.
- 3- Results represent sample submitted for test only.

Manager of Const. Labs Department

المالية المالية

Ve

# فحوصات المواد الأولية في مختبر خارجي معتمد من وزارة الأشغال

أسمنت عادي (كيميائي + فيزيائي) أسمنت مقاوم (كيميائي + فيزيائي) المادة المضافة (كيمياء+ فيزيائي) الرمل المغسول (كيميائي + فيزيائي) صلبوخ ۳/۲ inch (كيميائي + فيزيائي) صلبوخ ۳/۲ inch (كيميائي + فيزيائي) صلبوخ ۳/۲ inch (كيميائي + فيزيائي)





P.O. Box: 24993, Safat 13110, Kuwait

Tel №: 00965 24748859 / 24733048 / 24735121; Fax №: (+965) 24733045

E-mail: Im@glico.net / Website: www.glico.net

## **CHEMICAL TESTS ON AGGREGATE SAMPLES**

Client

: Al-Jazeera Ready Mix

Description

: Agg. 3/8 Lime Stone

**Date of Test** 

: 14-Jun-2023

Date of Report : 18-Jun-2023

GII Job Ref. No : 2023 06 01157

Sample	TEST	Res	sult	Ref Standard
		(%)	ppm	Rei Stalldard
Agg. 3/8 Lime	Water Soluble ChlorideContent	0.0159	159	BS 812-117
Stone	Acid Soluble Sulphate Content	0.0412	412	BS 812-118

## Remarks:


· Result represent the sample submitted for test only.

Tested by:

Chemist

Checked by:

Laboratory Engineer



SIEVE	PERCENT FINER	SPEC.* PERCENT	PASS?
12.5	100.0		
9.5	96.6		
4.75	15.1		
2.36	1.2		
1.18 0.075	0.9 0.6		
0.075	0.0		

Coarse

0.0

0.0

Fine

84.9

Coarse

14.0

Medium

0.3

Fine

0.2

	Material Descript	ion	
Aggregate 3/8	inch		
PL=	Atterberg Limit	<b>S</b> P =	
	Classification		
USCS=	AASHT	0=	
	Remarks		
Sample Receive	d Date: 07-06-2023		
Test Date: 10-06			
Report Date: 17-	-06-2023		
	anual/Mechanical		
Balance: S.No.			
Hydrometer: S.N			
	r. C. No. GM is all	1	

GULF INSPECTION INTERNATIONAL CO.

Client: Aljazeera Industrial Ready Mix Concrete.

Project: For factory approval

Project No: 20230601157

Figure VV 1 LAB APPROVAL # Q4385

S Date:

Clay

0.6

Tested By: Laboratory Technician Checked By: Laboratory Manager



P.O. Box : 24993, Safat 13110, Kuwait Tel. : 00965 24748859 / 24733048 / 24735121; Fax : 24733045 E-mail : Im@glico.net; Web : www.glico.net

## REPORT OF CHEMICAL TEST ON CEMENT SAMPLE IN ACCORDANCE WITH ASTM C 150/C-114

Client: Al-Jazerra Ready Mix

Testing Date: 14-Jun-2023

Reporting Date: 19-Jun-2023

Job Ref № : 2023 06 01157

Sample Description: Ordinary Portland Cement

Test	Result %	Specification Limit
SiO2	21.30	-
Fe2O3	3.15	
Al203	3.36	Section 1
CaO	62.45	-
MgO	3.19	6 % Max
SO3	2.44	3 % Max
Na2O	0.08	
K20	0.65	
Alkalis Equvalent (Na2O+.658K2O)	0.51	0.6 % Max
Insoluble Residue	0.49	0.75 % Max
Loss on Ignition	2.05	3 % Max
СЗА	3.57	-
C3S	58.32	
C2S	17.07	
C4AF	9.59	
C4AF +2(C3A)	16.72	25 % Max

Remark:

\* Result represent the sample submitted for test by client only.

Tested by :

Chemist

Checked by:



P.O. Box: 24993, Safat 13110, Kuwait Tel.: 00965 24748859 / 24733048 / 24735121; Fax: 24733045

E-mail: Im@giico.net; Web: www.giico.net

## Normal Consistency of Hydraulic Cement by Vicat Needle (ASTM C 187)

Client Name : Aljazeera Industrial Ready Mix Concrete.

Project Name: For factory approval

Testing Date : 13/Jun/23

Reporting Date: 17/Jun/23

Job Ref № : 2023 06 01157

Sample Description: OPC Cement / 0001909

Sr. No.	% of Water	Amount of Water (ml)	Penetration in 30 Sec. (mm)
1	25	162.5	4
2	27	175.5	6
3	31	201.5	9

### Remark:

- \* Results represent the samples submitted by Client for test only.
- \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.
- \* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

Lab Technician

proved by:

Laboratory Manager



P.O. Box: 24993, Safat 13110, Kuwait Tel.: 00965 24748859 / 24733048 / 24735121; Fax: 24733045

E-mail: Im@gilco.net; Web: www.gilco.net

## Time of setting of hydraulic cement by vicat needle (ASTM C 191-19)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name : For factory approval

Testing Date: 13/Jun/23

Reporting Date: 17/Jun/23

Job Ref № : 2023 06 01157

Sample Description : OPC Cement / 0001906

1	Mass of Cement		650	(g)
2	Mass of Water		171.3	(ml)
3	Time of Last Penetration greater than 25mm	E	65	(min)
4	Time of Last Penetration less than 25mm	Н	75	(min)
5	Penetration Reading at Time E	С	27	(mm)
6	Penetration Reading at Time H	D	22	(mm)
7	Inital Time of Setting		69	(min)
8	Final Time of Setting		256	(min)

## Remark:

- \* Results represent the samples submitted by Client for test only.
- \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.
- \* GIIÇO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by

Lab Technician

Approved by:

Laboratory Manager



Tel.: 00965 - 24748859 / 24735121 / 24733048; Fax: 24733045 Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61 E-mail: Im@giico.net; Web: www.giico.net

# REPORT ON COMPRESSIVE STRENGTH OF GROUT CUBES (ASTM C 942/ASTM C 109)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name: For factory approval

Test Date: 17-06-23 Report Date: 18-06-23

Report Ref.: 2023 06 01157 Grade: SRC Cement

Machine No.: 1-03094826

Expired of Calibration: 03/09/2023

-	Dim	Dimensions (mm)	(mm	Date of	Date of	Age	Weight	Density	Load	Stre	Strength
Sample ID	-	8	H	Cast	Test	(days)	(6)	(g/cm3)	(kN)	(N/mm2)	(kg/cm2)
1	50	50	50	14-06-23	17-06-23	3	276.6	2.213	42.3	16.9	172
4	20	20	20	14-06-23	17-06-23	3	274.8	2.198	49.3	19.7	201
			- N								
									3 3 3 3		
				The state of the s		Thens Mr.					
									Average	18.3	187

# Remarks:

\* Results represent the samples submitted by Client for test only.

\* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.

\* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by res

LAB APPROVA W:\Z0233\G41 - PROJECT REPORTS\Daily Clients\06- June 2023\Z023 06 01157\_Aljazeera Industrial Ready Mix Concrete.(Physical & Chemical tests 1\2023 06 01157\_drouply 04 Issue date: June 2010

Issue no: 1



Tel.: 00965 - 24748859 / 24735121 / 24733048; Fax: 24733045 E-mail: Im@glico.net; Web: www.glico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

# REPORT ON COMPRESSIVE STRENGTH OF GROUT CUBES (ASTM C 942/ASTM C 109)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name: For factory approval

Test Date: 21-06-23 Report Date: 22-06-23

Report Ref.: 2023 06 01157 Grade: SRC Cement

Machine No.: 1-03094826 Expired of Calibration: 03/09/2023

	Dim	Dimensions (mm)	(mm	Date of	Date of	Age	Weight	Density	Load	Stre	Strength
Sample ID	1	8	Ξ	Cast	Test	(days)	(6)	(g/cm3)	(kN)	(N/mm2)	K
2	20	50	20	14-06-23	21-06-23	7	276.5	2.212	61.3	24.5	250
2	50	20	20	14-06-23	21-06-23	7	276.2	2.210	57.4	23.0	235
				100000000000000000000000000000000000000						Description of the second	
							STATE STATE				
						No. of Persons Street, St.					
									TOWN VETTIN		
				A COUNTY OF THE PARTY OF THE PA	THE RESIDENCE						
									Average	e 23.8	243

# Remarks:

- \* Results represent the samples submitted by Client for test only.
- ed within the contract agreement. \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery ,
  - \* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized

W:\2023\G41 - PROJECT REPORTS\Daily Clients\06- June 2023\2023 06 01157\_Aljazeera Industrial Ready Mix Concrete.(Physical & Chemical tests)\2023 06 01157\_Grout 06hos SRG(3,7,28 LAB APPROVAL # Q4185

Issue date: June 2010

Issue no: 1



P.O. Box : 24993, Safat 13110, Kuwait Tel. : 00965 24748859 / 24733048 / 24735121; Fax : 24733045 E-mail : Im@glico.net; Web : www.glico.net

# REPORT OF CHEMICAL TEST ON CEMENT SAMPLE IN ACCORDANCE WITH ASTM C 150/C-114

Client: Al-Jazerra Ready Mix

Testing Date: 14-Jun-2023

Reporting Date: 19-Jun-2023

Job Ref № : 2023 06 01157

Sample Description : Sulphate Resistant Cement

Test	Result %	Specification Limit
SiO2	22.05	
Fe2O3	4.39	
Al2O3	3.8	
CaO	63.89	
MgO	2.09	6 % Max
SO3	1.89	3 % Max
Na2O	0.07	
K20	0.59	
Alkalis Equvalent (Na2O+.658K2O)	0.46	0.6 % Max
Insoluble Residue	0.55	0.75 % Max
Loss on Ignition	1.88	3 % Max
C3A	2.64	5 % Max
C3S	55.32	-
C2S	21.48	
C4AF	13.36	
C4AF +2(C3A)	18.63	25 % Max

Remark:

ested by :

\* Result represent the sample submitted for test by client only.

Chemist

Checked by :

Laboratory Manager



P.O. Box : 24993, Safat 13110, Kuwait Tel. : 00965 24748859 / 24733048 / 24735121; Fax : 24733045

E-mail: Im@giico.net; Web: www.giico.net

## Normal Consistency of Hydraulic Cement by Vicat Needle (ASTM C 187)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name : For factory approval

Testing Date: 14/Jun/23

Reporting Date : 17/Jun/23

Job Ref № : 2023 06 01157

Sample Description : SRC Cement / 0001906

Sr. No.	% of Water	Amount of Water (ml)	Penetration in 30 Sec. (mm)
1	22	143	4
2	26	169	7
3	30	195	11

## Remark:

- \* Results represent the samples submitted by Client for test only.
- \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.
- \* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

Lab Technician

Approved by :

IMP W I

aboratory Manage

LAD ADSDOUNT & OFFICE



P.O. Box: 24993, Safat 13110, Kuwait Tel.: 00965 24748859 / 24733048 / 24735121; Fax: 24733045

E-mail: Im@glico.net; Web: www.glico.net

## Time of setting of hydraulic cement by vicat needle (ASTM C 191-19)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name : For factory approval

Testing Date: 15/Jun/23

Reporting Date : 17/Jun/23

Job Ref № : 2023 06 01157

Sample Description : SRC Cement / 0001909

1	Mass of Cement		650	(g)
2	Mass of Water		165.8	(ml)
3	Time of Last Penetration greater than 25mm	Е	133	(min)
4	Time of Last Penetration less than 25mm	Н	141	(min)
5	Penetration Reading at Time E	С	27	(mm)
6	Penetration Reading at Time H	D	24	(mm)
7	Inital Time of Setting		138	(min)
8	Final Time of Setting		292	(min)

## Remark:

- \* Results represent the samples submitted by Client for test only.
- \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.
- \* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

Lab Technician

Approved by :

**Laboratory Manager** 



Tel.: 00965 - 24748859 / 24735121 / 24733048; Fax: 24733045 E-mail: Im@glico.net; Web: www.glico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

# REPORT ON COMPRESSIVE STRENGTH OF GROUT CUBES (ASTM C 942/ASTM C 109)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name: For factory approval

**Test Date:** 17-06-23

Report Date: 18-06-23 Report Ref.: 2023 06 01157

Grade: OPC Cement

Machine No.: 1-03094826 Expired of Calibration: 03/09/2023

Sample TD	Dim	Dimensions (mm)	(mm)	Date of	Date of	Age	Weight	Density	Load	Stre	Strength
	7	8	Ξ	Cast	Test	(days)	(6)	(g/cm3)	(kN)	(N/mm2)	(kg/cm2)
1	20	20	50	14-06-23	17-06-23	3	280.9	2.247	59.2	23.7	242
4	50	20	20	14-06-23	17-06-23	3	281.8	2.254	55.6	22.2	226
											Manage Inches
		7									
							THE REAL PROPERTY.		Average	23.0	234

# Remarks:

\* Results represent the samples submitted by Client for test only.

thin the contract agreement. \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated in

\* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by respective client

W:\2023\G41 - PROJECT REPORTS\Daily Clients\06- June 2023\2023 06 01157\_Aljazeera Industrial Ready Mix Concrete.(Physical & Chemical tests )\2023-06 01157\_Group 36nbs. Option 10 of the contract of the contr

Issue date: June 2010

LAB APPROV

Days) Issue no: 1



Tel.: 00965 - 24748859 / 24735121 / 24733048; Fax: 24733045 Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61 E-mail: Im@giico.net; Web: www.giico.net

# REPORT ON COMPRESSIVE STRENGTH OF GROUT CUBES (ASTM C 942/ASTM C 109)

Client Name: Aljazeera Industrial Ready Mix Concrete.

Project Name: For factory approval

Test Date: 21-06-23

Report Ref.: 2023 06 01157 Report Date: 22-06-23

Grade: OPC Cement

Machine No.: 1-03094826

Expired of Calibration: 03/09/2023

(days) (g) (g/cm3)
7 281.3 2.250

# Remarks:

\* Results represent the samples submitted by Client for test only.

otherwise stated within the contract agreement. \* The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless

\* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized official

W:\2023\G41 - PROJECT REPORTS\Daily Clients\06- June 2023\2023 06 01157\_Aljazeera Industrial Ready Mix Concrete.(Physical & Chemical tests)\2023 06 01157\_Group 06ngs\_Onc (3.7.7) LAB APPROV

Issue date: June 2010

Issue no: 1





P.O. Box : 24993, Safat 13110, Kuwait

Tel №: 00965 24748859 / 24733048 / 24735121; Fax №: (+965) 24733045

E-mail: Im@giico.net / Website: www.giico.net

## TEST OF CONCRETE ADMIXTURE AS PER ASTM C494/C494M-16

Client

Al-Jazeera Ready Mix

Date of Test :

17-Jun-2023

Date of Report :

25-Jun-2023

GII Job Ref NO:

2023 06 01157

S.No	Properties	Units	Control Mix.	Test Mix	Specification Limits
1	W/c	%	70	58	
2	Dosage as per Catalogue	Litre/m³		2.46	
3	Water Content	Litre/m³	215	178	
4	Water Percent to Contorol	%	100	83	88 % Max
5	Aggregate Content	Kg/m³	290	290	All Moley
6	Sand Content	Kg/m³	675	675	
7	Cement Content	Kg/m³	305	305	
8	Sulmp test (ASTM C 143/10a)	Cm	9.0	10.3	9.0± 1.5
	Compressive Strength test (B	S 1881 Part 1:	16/83)		
9	3 DAYS	Kgf/Cm <sup>2</sup>	151	199	
9	7 DAYS	Kgf/Cm <sup>2</sup>	192	248	N. STATE
	28 DAYS	Kgf/Cm <sup>2</sup>			
	Compressive Strength To Contr	rol Percentage			
10	3 DAYS	%	100	132	125 Min
10	7 DAYS	%	100	129	115 Min
	28 DAYS	%	100		110 Min
11	Temperature	C.	23	23	
12	Air Content Test (ASTM C 231/1	10a)	The state of		
12	Air Content	9/0	1.5	1.8	

## Remarks:

· Results represent sample submitted for test only.

Approved by :



BSI (I)

P.O. Box : 24993, Safat 13110, Kuwait Tel №: 00965 24748859 / 24733048 / 24735121; Fax №: (+965) 24733045

E-mail: Im@glico.net / Website: www.glico.net

## **Chemical Admixture Uniformity Test**

Client

: Al-Jazeera Ready Mix

Description

: Chemical Admixture For Concrete (EPOCON SP 545)

Date of Test

: 14-Jun-2023

Date of Report

: 18-Jun-2023

GII Job Ref. №

: 2023 06 01157

TEST	Result	Ref Standard
Dry material content (Residue by oven drying)	42.10%	ASTM C 494
Specific gravity	1.22	ASTM C 494

## Remarks:

· Result represent the sample submitted for test only.

Tested by:

Chemist

Approved by:

Laboratory Manage



P.O. Box : 24993, Safat 13110, Kuwait Tel №: 00965 24748859 / 24733048 / 24735121; Fax №: (+965) 24733045 E-mail: Im@giico.net / Website: www.giico.net

## **CHEMICAL TESTS ON AGGREGATE SAMPLES**

Client

: Al-Jazeera Ready Mix

Description

: Washed Sand

Date of Test

: 14-Jun-23

Date of Report

: 19-Jun-23

GII Job Ref. №

: 2023 06 01157

Sample	TEST	Re	sult	Ref Standard
**************************************	BELLEVILLE SAN	(%)	ppm	Rei Standard
Washed Sand	Water Soluble Chloride Content	0.011	110	BS 812-117
wasileu saliu	Acid Soluble Sulphate Content	0.0516	516	BS 812-118

## Remarks:

- Result represent the sample submitted for test by client only.


- GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

Chemist

Approved by :

Laboratory Manager
MPW 1



0/ 128	% Gravel		% Sand			% Fines	
% +3"	Coarse	Fine	Coarse	Medium	Fine	Silt	Clay
0.0	0.0	1.0	6.2	49.0	41.5	2.3	

SIEVE	PERCENT	SPEC.*	PASS?
SIZE	FINER	PERCENT	(X=NO)
9.5	100.0		
4.75	99.0	A SECTION OF THE PARTY OF THE P	
2.36	94.6	ALTONO THE	
1.18	84.7		
0.850	76.7		
0.600	60.9		
0.425	43.8		
0.300	24.4		
0.150	6.2		
0.075	2.3		

	Material Description	
Washed Sand		
PL=	Atterberg Limits	PI=
	Classification	
USCS=	AASHTO=	
	Remarks	
Sample Receive	d Date: 07-06-2023	
Test Date: 08-06		
Report Date: 17	-06-2023	
ALTER OF THE PARTY	anual/Mechanical	
Balance: S.No. 1		
Hydrometer: S.N	No. 118229	
1000ml Cylinder		

ASTM - C 136

Date:

GULF INSPECTION INTERNATIONAL CO.

Client: Aljazeera Industrial Ready Mix Concrete.

Project: For factory approval

Project No: 20230601157

Figure

Checked By: Laboratory Manager





Tel №: (+965) 24748859 / 24735121 / 24733048; Fax №: 24733045

E-mail: Im@giico.net; Web: www.giico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

# REPORT ON SPECIFIC GRAVITY AND ABSORPTION OF AGGREGATE ASTM C 127 / C 128

Client : Aljazeera Industrial Ready Mix Concrete.

Project : For factory approval

Sample Desc. : Washed Sand

Test Date: 13/Jun/2023

Report Date: 17/Jun/2023

Report Ref. Nº: 2023 06 01157

SPECIFIC GRAVITY AND ABSORPTION OF COARSE AGGREGATE							
Item	Description	1	2	3	Average		
Α	Weight of Oven Dry Sample (g)				/		
В	Weight of SSD Sample (g)						
С	Weight of Submerged Sample (g)						
D	Bulk Specific Gravity (OD Basis)	es de entre en	/				
E	Bulk Specific Gravity (SSD Basis)	Paris May 2					
F	Apparent Specific Gravity						
G	Absorption (%)						

Item	Description	1	2	3	Average
Α	Weight of Oven Dry Sample (g)	100.20			
В	Weight of SSD Sample (g)	100.75		95 PO	582
С	Weight of Bottle + Water + Sample (g)	446.57			
D	Weight of Bottle + Water (g)	384.80			
E	Bulk Specific Gravity (OD Basis)	2.571			2.571
F	Bulk Specific Gravity (SSD Basis)	2.585	MAN 94 W	Charles of A	2.585
G	Apparent Specific Gravity	2.607			2.607
Н	Absorption (%)	0.55	The Parket		0.55

Remarks

\* Result represent the sample submitted for test by client only

\* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

p. .

Laboratory Technician

Approved by :

aboratory Manager

Issue no: 1

Issue date: June 2010



Tel.: 00965 24748859 / 24735121 / 24733048; Fax: 24733045

E-mail: Im@giico.net; Web: www.giico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

## SAND EQUIVALENT - ASTM D2419

Client: Aljazeera Industrial Ready Mix Concrete.

Project: For factory approval

Sample Description: Washed Sand

Test Date: 08/Jun/2023 Report Date: 17/Jun/2023

Report Ref. №: 2023 06 01157

Test No.	Sand Reading	Clay Reading	(Sand Reading/ Clay Reading)*100	Sand Equivalent
1	3.8	6.7	56.72	57
2	3.8	6.6	57.58	58
3	3.9	6.8	57.35	58
			Average	58

Remark: - Result represent the sample submitted for test by client only

- GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

**Laboratory Technician** 

Approved by :

Laboratory Manager



Tel.: 00965 24748859 / 24735121 / 24733048; Fax: 24733045 E-mail: Im@giico.net; Web: www.giico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

# REPORT ON SOUNDNESS OF AGGREGATES (ASTM C88 - 18 / AASHTO T-104)

Project: Aljazeera Industrial Ready Mix Concrete.

Client Name: For factory approval

Sample Desc.: Washed Sand

Test Date: 04-Jun-2023 Report Date: 18-Jun-2023 Report Ref. Nº: 2023 06 01157

Sieve Size	Grading of Original Sample, %	Wt of Sample Before Test, g	Wt of Sample After Test, g	Wt of Sample Passing Designated Sieve, g	% Passing Designated Sieve	Weighted % Loss
SOUNDNESS TEST OF FINE AGGREGATE						
Passing 150 µm (No. 100)	6.2	100.2	88.5	11.7	11.7	0.72
300 µm (No. 50) to 150 µm (No. 100)	18,2	100.1	91.2	8.9	8.9	1,618
600 µm (No. 30) to 300 µm (No. 50)	36.5	100.2	92.6	4.6	4.6	1.676
1.18 mm (No. 16) to 600 µm (No. 30)	23.8	100.0	97.4	2.6	2.6	0.619
2.36 mm (No. 8) to 1.18 mm (No. 16)	6.6	100.1	986	1.5	1.5	0.148
4.75 mm (No. 4) to 2.36 mm (No. 8)						
9.5 mm (3/8 inch) to 4.75 mm (No. 4)						
					Total	4.785
SOUNDNESS TEST OF COARSE AGGREGATE	TE					
63 mm (2 1/2 inch) to 50 mm (2 inch)						
50 mm (2 inch) to 37.5 mm (1 1/2 inch)					1	
37.5 mm (1 1/2 inch) to 25 mm (1 inch)						
25 mm (1 inch) to 19 mm (3/4 inch)						
19 mm (3/4 inch) to 12.5 mm (1/2 inch)		1				
12.5 mm (1/2 inch) to 9.5 mm (3/8 inch)						
9.5 mm (3/8 inch) to 4.75 mm (No. 4)	\					
					Total	

Remarks: - Freshly prepared SO4 solution used for the test.

Result represent the sample submitted for test by client only.

- The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.

GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

Laboratory Technician

W12023(641 - PROJECT REPORTS/Daily Clients/06- June 2023/2023 06 01157\_Aljazeera Industrial Ready MixRomertDe APIG-SRad. & Chemical tests )/2023 06 01157\_Soundness Test\_(Washed Sand)Ino.45

Laboratory Manager



P.O. Box: 24993, Safat 13110, Kuwait

Tel №: 00965 24748859 / 24733048 / 24735121; Fax №: (+965) 24733045

E-mail: Im@giico.net / Website: www.giico.net

## **CHEMICAL TESTS ON AGGREGATE SAMPLES**

Client

: Al-Jazeera Ready Mix

Description

: Agg. 3/4 Lime Stone

**Date of Test** 

: 14-Jun-2023

Date of Report

: 18-Jun-2023

GII Job Ref. Nº : 2023 06 01157

Sample	TEST	Res	Ref Standard		
Сатріс	1251	(%)	ppm	Kei Standard	
Agg. 3/4 Lime Stone	Water Soluble ChlorideContent	0.0138	138	BS 812-117	
	Acid Soluble Sulphate Content	0.0438	438	BS 812-118	

## Remarks:


· Result represent the sample submitted for test only.


Tested by:

Chemist

checked by:

**Laboratory Engineer** 





GRAIN SIZE - mm.							
	% Gr	avel	% Sand			% Fines	
% +3"	Coarse	Fine	Coarse	Medium	Fine	Silt	Clay
0.0	7.0	92.7			0.	3	

SIEVE	PERCENT	SPEC.* PERCENT	PASS? (X=NO)
25	100.0		
19	92.9	MINISTER AND	
12.5	23.6		
9.5	4.0		
4.75	0.3		
0.075	0.3		
	LINE A SE	N. BERT	

	Material Description	
Aggregate 3/4	inch	
	Atterberg Limits	
PL=	LL=	PI=
	Classification	
USCS=	AASHTO=	
	Remarks	
Sample Receive	ed Date: 07-06-2023	
Test Date: 10-0	6-2023	
Report Date: 17	-06-2023	
Test Method: M	Ianual/Mechanical	
Balance: S.No.	171110058	
Hydrometer: S.1	No. 118229	
1000ml Cylinde	er: C. No. GM-1	

ASTM - C 136

Date:

GIIC-07-08-03

GULF INSPECTION INTERNATIONAL CO.

Client: Aljazeera Industrial Ready Mix Concrete.

Project: For factory approval

Project No: 20230601157

Figure

Tested By: Laboratory Technician

Checked By: Laboratory Manager





Tel № : (+965) 24748859 / 24735121 / 24733048; Fax № : 24733045 E-mail : Im@glico.net; Web : www.glico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

## REPORT ON SPECIFIC GRAVITY AND ABSORPTION OF AGGREGATE ASTM C 127 / C 128

Client: Aljazeera Industrial Ready Mix Concrete.

Test Date: 13/Jun/2023

Project : For factory approval

Report Date: 17/Jun/2023

Sample Desc. : Aggregate 3/4 inch

Report Ref. Nº: 2023 06 01157

Item	Description	1	2	3	Average
Α	Weight of Oven Dry Sample (g)	5106.70			
В	Weight of SSD Sample (g)	5129.30			
С	Weight of Submerged Sample (g)	3229.50			
D	Bulk Specific Gravity (OD Basis)	2.688		Jav Klari	2.688
Е	Bulk Specific Gravity (SSD Basis)	2.700			2.700
F	Apparent Specific Gravity	2.720			2.720
G	Absorption (%)	0.443	or fall		0.443

Item	Description	1	2	3	Average
Α	Weight of Oven Dry Sample (g)				
В	Weight of SSD Sample (g)			The state of	
С	Weight of Bottle + Water + Sample (g)	The Control of			
D	Weight of Bottle + Water (g)				
E	Bulk Specific Gravity (OD Basis)		/		
F	Bulk Specific Gravity (SSD Basis)				
G	Apparent Specific Gravity	/		A Hard	TIME
Н	Absorption (%)	/	Affile and	THE WAY IN	

Remarks

\* Result represent the sample submitted for test by client only

\* GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless

it is authorized officially by client respective.

Tested by:

Per.

Laboratory Technician

Approved by :

Laboratory Manager



P.O. Box: 24993, Safat 13110, Kuwait

Phone №: +965 24748859 | 24733048 | 24735121 | Fax №: 24733045 E-mail : Im@giico.net; Web : www.giico.net

# REPORT ON UNIT WEIGHT OF COARSE AGGREGATE (ASTM-C-29/C29M)

Client: Aljazeera Industrial Ready Mix Concrete.

Project : For factory approval Sample Desc. : Aggregate 3/4 inch

DATE OF TEST: 14/Jun/2023

DATE OF REPORT: 18/Jun/2023

GIICO JOB №: 2023 06 01157

## MEASURING CYLINDER

WEIGHT (g): 2938.0 VOLUME (cm<sup>3</sup>): 2802.3

## I) RODDING

Trial No.	Wt of Aggregate + Cylinder (g)	Wt of Aggregate in Cylinder (g)	Bulk Density of Agg. (g/cm3)
1	7352.4	4414.4	1.575
2	7355.9	4417.9	1.577
3	7348.8	4410.8	1.574
tra-1941 Toronto		Average	1.575

## 2) JIGGING

Trial No.	Wt of Aggregate + Cylinder (g)	Wt of Aggregate in Cylinder (g)	Bulk Density of Agg. (g/cm3)
1	7128.3	4190.3	1.495
2	7140.8	4202.8	1.500
3	7136.6	4198.6	1.498
		Average	1.498

## **REMARKS:**

\* Result represent the sample submitted for test by client only

Tested by:

**Laboratory Technician** 

Laboratory Manager

proved by:

W:\2023\G41 - PROJECT REPORTS\Daily Clients\06- June 2023\2023 06 01157\_Aljazeera Industrial Ready Mix Concrete Physical & Chemical tests )\2023 06 01157\_Unit Weight of Agg. Mix



Tel.: 00965 4748859 / 4735121 / 4733048; Fax: 4733045 E-mail: soilwell@qualitynet.net; Web: www.giico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

## Determination of Aggregate Impact Value (BS 812:112)

Project : For factory approval Test Date : 10-06-2023

Client: Aljazeera Industrial Ready Mix Concrete. Report Date : 17-06-2023

Sample Desc: Aggregate 3/4" Report Ref.: 2023 06 01130

Aggregate Size: (14.0 to 10.0) mm

Description	1st Trial	2nd Trial
A - Weight of Test Fraction Before (g)	341.9	343.7
B - Weight of Material Passing 2.360 mm Sieve (g)	93.3	93
C - Aggregate Impact Value (%)	27.29	27.06
D - Avg. Aggregate Impact Value (%)	27	1.17

## Remarks:

- Result represent the sample submitted for test by client only.
- The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.
- GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respective.

Tested by:

Sr Lab Technician

TO THE RESERVE OF THE PARTY OF

Checked by:

Laboratory Manager



Tel.: 00965 4748859 / 4735121 / 4733048; Fax: 4733045 E-mail: soilwell@qualitynet.net; Web: www.giico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

## REPORT ON RESISTANCE TO DEGRADATION OF SMALL-SIZE COARSE AGGREGATE BY ABRASION AND IMPACT IN THE LOS ANGELES MACHINE (ASTM C 131)

Client: Aljazeera Industrial Ready Mix Concrete.

Test Date: 13-Jun-2023

Project: For factory approval

Report Date: 17-Jun-2023

Sample Desc. : Aggregate 3/4 inch

Report Ref. Nº: 2023 06 01157

**Grading of Test Sample** 

Sieve Size			GRAD	ING	
Passing	Retained on	A	В	C	D
37.5 mm (1-1/2 in)	25.0 mm (1 in)				
25.0 mm (1 in)	19.0 mm (3/4 in)				
19.0 mm (3/4 in)	12.5 mm (1/2 in)		2505.3		
12.5 mm (1/2 in)	9.5 mm (3/8 in)		2503.9	RELEASE THE	
9.5 mm (3/8 in)	6.3 mm (1/4 in)				
6.3 mm (1/4 in)	4.75 mm (No. 4)				
4.75 mm (No. 4)	2.36 mm (No. 8)				
	TOTAL		5009.2		

Weight of sample of taken for testing 5009.2 g

Weight of sample remaining over \_\_\_\_\_\_ 3738.5 g

1.70 mm sieve (after testing)

The above test results represent the sample submitted for testing only

Tested by:

Percentage loss by abrasion and impact

Laboratory Technician



Approved by:

25.37 %

THE STATE OF THE S

Laboratory Manager



Tel.: 00965 24748859 / 24735121 / 24733048; Fax: 24733045 E-mail: Im@giico.net; Web: www.giico.net Sabhan Industrial Area; Block: 6; Plot: 57; Street: 61

# REPORT ON SOUNDNESS OF AGGREGATES (ASTM C88 - 18 / AASHTO T-104)

Project: Aljazeera Industrial Ready Mix Concrete.

Client Name: For factory approval

Sample Desc. : Aggregate 3/4 inch

Test Date: 10-Jun-2023 Report Date: 17-Jun-2023 Report Ref. Nº: 2023 06 01157

						The state of the s
Sieve Size	Grading of Original Sample, %	Wt of Sample Before Test, g	Wt of Sample After Test, g	Wt of Sample Passing Designated Sieve, g	% Passing Designated Sieve	Weighted % Loss
SOUNDNESS TEST OF FINE AGGREGATE						
Passing 150 μm (No. 100)						
300 µm (No. 50) to 150 µm (No. 100)						1
600 µm (No. 30) to 300 µm (No. 50)				1		
1.18 mm (No. 16) to 600 µm (No. 30)						
2.36 mm (No. 8) to 1.18 mm (No. 16)			\			
4.75 mm (No. 4) to 2.36 mm (No. 8)						
9.5 mm (3/8 inch) to 4.75 mm (No. 4)						
					Total	
SOUNDNESS TEST OF COARSE AGGREGATE	TE					
63 mm (2 1/2 inch) to 50 mm (2 inch)						
50 mm (2 inch) to 37.5 mm (1 1/2 inch)						
37.5 mm (1 1/2 inch) to 25 mm (1 inch)						
25 mm (1 inch) to 19 mm (3/4 inch)						
19 mm (3/4 inch) to 12.5 mm (1/2 inch)	88.9	1001.4	995.2	6.2	0.619	0.550
12.5 mm (1/2 inch) to 9.5 mm (3/8 inch)			The sale of the sa			
9.5 mm (3/8 inch) to 4.75 mm (No. 4)						
					. Total	0.550

Remarks: - Freshly prepared MgSO4 | Magnesium sulfate solution used for the test.

- Result represent the sample submitted for test by client only.

- The validity period of this document/report is (1) month, to be measured from the date of its final submission/delivery unless otherwise stated within the contract agreement.

- GIICO Lab is responsible for the confidentiality of the report and shall not disclose it any party Unless it is authorized officially by client respect

Tested by:

Laboratory Technician

aboratory recrimeran

LAB APPROVAL 3 W:\2023\G41 - PROJECT REPORTS\Daily Clients\06- June 2023\2023 06 01157\_Aljazeera Industrial Ready MixRomonthe Apid-Stab. & Chemical tests \\2023 06 01157\_ Soundness Test\_ (Agg. 3-4)1no.

aboratory Manager



- ✓ info@jazeerakw.com
- **L** +965 9222 6858 +965 9994 006
- © @jazeera.kw
- kabad Block B Building 7